



Scenic Flat® Super Saturated

PaintPlus Scenic Flat® is a custom formulation for the scenic set artist. It may be used straight from the pail as an intense, opaque finish, reduced with white to produce undertones, intermixed with other colours from the range or diluted with water to create translucent effects and colour washes.

Product features

Self priming on most substrates

It dries to a flexible finish even when it is applied in thin coatings or highly diluted

The sheen levels of Scenic Flat® are extremely low creating a very flat finish to minimise light reflection

It is virtually odourless making it easy to work with and kind on the environment

Scenic Flat® is available in a range of cost-effective super-saturated colours

Typical areas of use

Canvas

Concrete

Brick

Fabric

Paper faced wallboard

Polystyrene

Plywood

Pressed chip board

Wood

Precautions

Not suitable for short term exterior applications

Environmental qualities

Manufactured in a carbon neutral certified facility – ISO 14064-1

VOC 3-4 gms per litre EC07-13

Ecolabel certified – Environmental Choice EC07-13

Licence number 0703012

Colour and gloss

Gloss level and description – flat 2% @ 60 degrees

Super Saturated Colours

Black, white, bright yellow, golden yellow, yellow ochre, bright red, orange, red oxide, burgundy, cyan blue, magenta, ultramarine, violet, cyan green, forest green, green oxide, lime, meadow green, raw sienna, burnt sienna, raw umber, burnt umber, process blue

Safety

Read label before use and keep out of reach of children.

If medical advice is needed: have product container or label at hand.

Wear protective clothing such as overalls, goggles and gloves and ventilate working areas.

Wash any paint deposits off skin.

If sanding wear face mask to avoid inhaling dust particles.

Application schedule

Drying and re-coat times are dependent on such factors as film thickness, atmospheric conditions, colour strength and dilution.

The general dry times are:

Touch dry 20 minutes

Re-coat time 30–60 minutes

Application is not recommended if the surface and/or air temperature is less than 10°C or is liable to fall below 10°C during the drying period.

Application methods

Good quality paint or cutting in brush

Medium nap roller – 14mm–16mm

Airless spray minimum 133 bars (2,000lb/sq in)

Tip size 15thou

Clean up and thinning

Clean up all equipment with water

Thin with potable water